

Multiple Stress Creep & Recovery								
Sample	Polymer %	Temperature	100Pa			3200Pa		
			Peak Strain	%Recover	Jnr	Peak Strain	%Recover	Jnr
Attock 60/70	0	58	0.452728	4.65	4.32	16.09746	0.25	5.02
		64	1.075334	2.02	10.54	38.2383	-0.55	12.02
		70	2.437684	-0.20	24.43	85.5465	-1.45	27.12
		76	5.50917	-0.28	55.25	221.7596	-4.17	72.19
	1.35	58	0.150491	56.26	0.66	4.70311	47.06	0.78
		64	0.302342	46.61	1.61	9.81176	27.95	2.21
		70	0.623902	35.01	4.05	22.3696	11.25	6.20
		76	1.25905	23.29	9.66	50.5663	3.33	15.28
	1.7	58	0.118456	74.29	0.30	3.57808	65.57	0.38
		64	0.20315	65.05	0.71	6.00907	52.46	0.89
		70	0.363844	59.15	1.49	11.29	36.55	2.24
		76	0.807749	46.66	4.31	29.9078	10.56	8.36
	2	58	0.107209	74.38	0.28	3.23899	67.81	0.33
		64	0.195142	65.82	0.67	5.87484	50.80	0.90
		70	0.369559	59.37	1.50	11.4365	34.70	2.33
		76	0.644283	49.96	3.22	22.1702	19.08	5.61
Karachi 60/70	0	58	0.350167	3.80	3.37	11.64598	0.01	3.64
		64	0.762283	1.58	7.50	25.3025	-0.47	7.94
		70	1.641916	0.54	16.33	54.5133	-1.02	17.21
		76	3.44802	7.62	31.85	125.65	-2.24	40.14
	2.5	58	0.177006	30.36	1.23	6.09725	7.54	1.76
		64	0.398188	46.21	2.14	14.86225	2.99	4.51
		70	0.824864	49.57	4.16	33.5241	0.56	10.42
		76	0.824864	49.57	4.16	70.0172	-0.79	22.05
	3.5	58	0.131896	2.8E+39	-3.8E+37	4.65614	20.09	1.16
		64	0.28575	60.84	1.12	10.75397	10.28	3.02
		70	0.546691	51.38	2.66	22.098	3.49	6.67
		76	1.110095	44.80	6.13	48.9929	0.75	15.20
	4.5	58	0.0919705	71.54	0.26	3.22458	32.92	0.68
		64	0.192335	70.62	0.57	7.25973	19.07	1.84
		70	0.401911	67.97	1.29	17.3096	6.78	5.04
		76	0.821501	58.37	3.42	39.3123	2.42	11.99
Karachi 80/100	0	58	0.481121	4.26	4.61	15.88516	-0.22	4.98
		64	1.000629	10.17	8.99	55.4103	-0.91	17.47
		70	2.229335	1.23	22.02	73.8689	-1.33	23.39
		76	4.47435	-1.00	45.19	148.7451	-2.64	47.71
Karachi 40/50	0	58	0.1858586	4.26	1.78	6.08292	0.59	1.89
		64	0.405721	3.28	3.92	13.3772	-0.09	4.18
		70	0.994924	1.46	9.80	32.6648	-0.62	10.27
		76	2.02036	0.69	20.06	22.1702	19.08	5.61
Attock 80/100	0	58	0.679781	11.05	6.05	26.1914	-0.13	8.20
		64	1.52269	1.90	14.94	55.4103	-0.91	17.47
		70	3.49082	-0.58	35.11	128.2502	-2.28	40.99
		76	6.59813	-1.86	67.21	250.4983	-4.73	81.99